BATEC

GBOARD®
RG



DESCRIPTION

Gboard® RG is a regular plasterboard ideal for general drywall and ceiling applications. It is a flexible gypsum board as it can accommodate any indoor architectural design.

It is composed of the best quality gypsum, extracted straight from our quarries, and processed using the best ecological practices.

All materials comply with ASTM 1396 and EN 520 standards and have been tested in accredited laboratories to ensure quality and performance.

APPLICATIONS

- Drywall partitions
- Suspended ceiling systems
- Wall lining
- Commercial or residential buildings
- Prefabricated constructions
- Malls, lounges, shops

FEATURES

- Easy and dry installation
- Eco-friendly, recyclable
- Lightweight
- No cracking
- Versatile
- Durable

Durable | Eco-friendly | No cracking | Lightweight

PROPERTIES

SURFACE FINISHING	EDGE TYPES	STANDARDS	DIMENSIONS
Painted (water or oil base paint) Cladding (wallpaper, vinyl, wood…) Joint filling with Gcoat™ All Purpose Joint Compound	Squared edge Tapered edge Beveled edge	ASTM C1396 EN520 ASTM C 473 ASTM C 518	Width 1200mm,1220mm Length 2000mm, 2400mm, 2440mm, 2500mm, 3000mm Thicknesses 8.0mm, 9.5mm 12.5mm, 15mm, 15.9mm, 18mm *Varying dimensions available upon request

Batiment Technique – BATEC, Hesya Industrial City, Homs, Syria
Tel : +963 987 215 617 www.batecgroup.com

PHYSICAL SPECIFICATIONS

SPECIFICATIONS	UNIT	VALUE	STANDARD
Thickness	mm	12.5	ASTM C 1396 / EN520
Density	Kg/m^3	650	ASTM C 1396 / EN520
Weight per unit area	Kg/m^2	8	ASTM C 1396 / EN520
Tolerance of length	mm	2401	ASTM C 1396 / EN520
Tolerance of width	mm	1200	ASTM C 1396 / EN520
Tolerance of thickness	mm	12.5	ASTM C 1396 / EN520
Depth of taper	mm	1.23	ASTM C 1396 / EN520
Width of taper	mm	42.57	ASTM C 1396 / EN520
Squareness of edges	mm	1.7	ASTM C 1396 / EN520
Core hardness	N	140	ASTM C 1396 / EN520
Edges hardness	N	110	ASTM C 1396 / EN520
Ends hardness	N	120	ASTM C 1396 / EN520
Flexural breaking load long edge	N	500	ASTM C 1396 / EN520
Flexural breaking load short edge	N	185	ASTM C 1396 / EN520
Nail pull strength	N	343	ASTM C 1396 / EN520
Bending radius	mm	1875	ASTM C 1396 / EN520
Humidified deflection	mm	1.4	ASTM C 1396 / EN520
Thermal conductivity	w/m.k	0.1839	ASTM C 518 / EN 12667

RECOMMENDATION

- Cutting and scoring are completed from the front face of the board.
- Use phosphate plated self-tapping screws with a metal frame <0.7mm for board fixing.
- Use phosphate plated self-drilling for a metal frame >0.7mm for board fixing.
- Vertical screw spacing for the first layer of gypsum is 25cm, 50cm for the second, and 75cm for the third.
- It is recommended to use Gcoat™ All Purpose Joint Compound to treat joints or for skim coating.

STORAGE AND HANDLING

- Avoid contact with moisture or temperatures higher than 50°C for prolonged periods of time.
- Store in a dry/ventilated area above ground level (not in direct contact with the ground).
- Cover the boards with plastic sheets.
- Avoid direct rain or sunlight.
- Avoid cracking or damaging the boards during installation.

The information herein and recommendations set forth are presented in good faith and believed to be correct as of the date hereof, BATEC-Batiment Technique, and its affiliated, and sister companies do not make representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving the same will make their own determination as to its suitability for their purpose prior to use. In no event will BATEC-Batiment Technique and its affiliated and sister companies be responsible for indirect, consequential, or incidental damages arising out of the use of, or inability to use this product. Our liability, if any, shall be capped to the price of the product purchased.

Manufactured according to ASTM & EN standards by BATEC-Batiment Technique under BEAM Consolidated.